

Revision: 1/2012
Page 1 of 2

SoudaSeal 50LM

Base	Silyl-terminated polymer	
Sag	No sag in vertical displ. @120°F	ASTM C 639
Curing system	Moisture Cure	
Tack-free time	90 minutes	ASTM C 679 (maximum 72 hours)
Cure time	24-72 hrs, ¼" diameter bead	@ 75°F & 50% relative humidity
Hardness – Shore A	25 +/- 5	ASTM C 661
Skin Formation (*) (75°F/50% RH)	<60 minutes	
Service temperature range	-40°F to +200°F	
Tensile Yield	188 psi	ASTM D 412
Elongation	>900%	ASTM D 412
Total joint movement	+/- 50%	ASTM C 719
Stain and color change	Passes	ASTM C 510 (no visible stain)
Artificial weathering	No Cracking	ASTM C 793 (2,000 hrs Xenonarc)
Shelf life	12 months	Stored between 41°F & 77°F

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates

Product:

SoudaSeal 50LM is a low-modulus and high movement SMX® joint sealant.

Characteristics:

- Tested and conform to ISO 11600-F-25LM
- excellent adhesion and extrudability, even in adverse conditions
- high bond strength on nearly all surfaces
- high performance mechanical properties
- flexible elastic rubber - movement accommodation up to +/- 50%
- low modulus - can handle extreme joint movement
- no bubble formation within sealant even in high temperature and humidity applications
- very easy to tool and finish
- color stable and UV resistant
- ecological advantages - free of isocyanates, solvents, halogens and acids
- minimal health and safety considerations
- can be painted with all water based paints and many other systems (to be tested)
- excellent weather resistance in all climates
- primerless adhesion on many different substrates (except where water pressure may occur)
- almost odorless

Applications:

- expansion and connection joints in the building industry
- sealing of joints in prefabricated buildings
- movement joints in high rise construction
- sealing between window and door frames
- flexible joints in marine and automotive applications
- applications that should be painted with water based paints

Colors:

Tan, stone, limestone, medium bronze, special bronze, hunter green, redwood, gray, aluminum gray, off white, white, black

Packaging:

10.1 fl. oz. cartridge; 20 fl. oz. sausages; 29 fl. oz. pro pack

Shelf life:

12 months in unopened packaging in a cool and dry storage place at temperatures between 41°F and 77°F

This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.



Revision 1/2012

Page 2 of 2

SoudaSeal 50LM

Substrates:

Recommended Surfaces: EIFS, Stucco, Aluminum, Concrete, Masonry, Wood, Stone, Glass, Vinyl, Fiber Cement Siding, Kynar Metals, PVC.

Surface Preparation: clean, dry, free of dust and grease, free of chipping paint

Priming: Porous surfaces in water loaded applications should be primed with Primer 150.

Surface activator may be used to pretreat non-porous surfaces.

Resistance to chemical agents:

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids, chlorinated hydrocarbons.

Joint dimensions:

Minimal Width: 1/16"

Maximum Width: 1 1/2"

Minimum Depth: 1/5"

Recommendation: width = 2 x depth

Remarks:

- should not be used as a structural sealant
- may be painted, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application. The drying time of alkyd resin based paints may increase.
- should not be used as a glazing sealant
- should not be used for continuous immersion in water
- do not apply to freshly treated wood; treated wood must have been weathered for at least 6 months
- lower temperatures and humidity will extend curing time

Application:

Method: Manual- or pneumatic caulking gun *Application temperature:* 34°F to 90°F *Cleaning:* with IPA immediately after use and before curing *Repair with:* SoudaSeal 50 LM

Meets:


ASTM C 920, Type S, Grade NS, Class 50, Use T, NT, M, A, G and O, Federal Specification TT-S-00230C, Type II, Class A

Health- and Safety Recommendation:

KEEP OUT OF REACH OF CHILDREN. Avoid skin and eye contact. On Contact, uncured sealant could cause irritation to skin and eyes. In case of eye contact, flush eyes with warm water for 15 minutes, call a physician. For skin contact, remove sealant with a paper towel. If swallowed, do not induce vomiting, call a physician. SoudaSeal 50 LM is manufactured for professional use only. Refer to Material Safety Data Sheet (MSDS) for further information.

Limited Warranty:

SODAL warrants product to be of good quality and will replace or, at our election, refund the purchase price of any products proved to be defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, SODAL MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and SODAL shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith.



**SEALANT · WATERPROOFING
& RESTORATION INSTITUTE**

Issued to: Soudal, Inc.
Product: SoudaSeal 50LM

C719: Pass Ext:+50% Comp:-50%

Substrate: Wood

C661: Rating 24

Validation Date: 11/15/11 – 11/14/16

No. 2011-50111511 Copyright © 2011

SEALANT VALIDATION
www.swrionline.org

This information and all further technical advice are based on SODAL present knowledge and experience. However, SODAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SODAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODAL reserves the right to make any changes according to technological progress or further developments.